## INDEXE

## **EUROPEAN PATENT OFFICE**

B13595/

## **Patent Abstracts of Japan**

**PUBLICATION NUMBER** 

2000303132

**PUBLICATION DATE** 

31-10-00

**APPLICATION DATE** 

20-04-99

**APPLICATION NUMBER** 

11111716

APPLICANT: SHINKO ARUKOA YUSO KIZAI KK;

INVENTOR: UEDA TOSHIKI;

INT.CL.


C22C 21/00

TITLE


: ALUMINUM ALLOY BRAZING SHEET

**EXCELLENT IN EROSION** 

CHARACTERISTIC



(A)



ABSTRACT :

PROBLEM TO BE SOLVED: To provide an Al alloy brazing sheet excellent in erosion characteristics and used, e.g. for automobile heat-exchanger parts material.

SOLUTION: A brazing filler metal 2, composed of an Al alloy containing 6.0-13.5% (by weight, the same applies to the following) Si or 0.4-5.5% Ge, is laminated on one side or both sides of a core material 1 composed of an Al alloy containing 0.05-2.0% Mn. The core material 1 is composed of an Al alloy further containing, besides Mn, 0.1-5.0% Ca, 0.1-10.0% Li, 0.05-0.8% Sr, 0.05-0.8% Sc, and 0.05-1.0% Y, and further one kind among prescribed amounts of Ti, Zr, V, Nb, Co, Ni, Ba, Be, and Ta. Because Be, etc., precipitate and fix, as compounds, Si and Ge which infiltrate from the brazing filler metal into the core material at the time of brazing, erosion can be controlled and prevented.

COPYRIGHT: (C)2000,JPO